

Comprehensive Technical Analysis of 1.7380 (10CrMo9-10) Steel: Properties, Engineering Applications, and Metallurgy

Published: October 9, 2026 | Index ID: #242

In the realm of high-temperature engineering and power generation, materials must withstand extreme thermal stresses, corrosive environments, and the relentless progression of creep. Among the most reliable alloys used for these demanding conditions is **1.7380**, also known by its chemical designation **10CrMo9-10**. This chromium-molybdenum alloy steel is a cornerstone in the construction of boilers, pressure vessels, and turbine components. Classified under the **EN 10273** and **EN 10216-2** standards, and frequently cross-referenced with the American **ASTM A335 P22** or **A182 F22** grades, 1.7380 offers a precise balance of weldability, creep resistance, and mechanical strength.

This technical analysis provides an exhaustive look into the metallurgical properties, heat treatment protocols, and industrial applications of 10CrMo9-10, serving as a definitive guide for materials engineers, procurement specialists, and structural designers.

1. Metallurgical Framework and Chemical Composition

The performance of 1.7380 is dictated by its specific alloying elements, primarily **Chromium (Cr)** and **Molybdenum (Mo)**. Chromium provides the necessary oxidation resistance and hardenability, while Molybdenum significantly enhances the material's creep-rupture strength at elevated temperatures. Unlike standard carbon steels, the addition of these elements allows the material to maintain its integrity at service temperatures reaching up to **580°C (1076°F)**.

The following table outlines the chemical composition requirements for 10CrMo9-10 as per the European EN standards:

Element	Percentage (%) Range
Carbon (C)	0.08 - 0.14
Silicon (Si)	max. 0.50
Manganese (Mn)	0.40 - 0.70
Chromium (Cr)	2.00 - 2.50
Molybdenum (Mo)	0.90 - 1.10
Phosphorus (P)	max. 0.025
Sulfur (S)	max. 0.020

The Role of Chromium and Molybdenum

The 2.25% Chromium content is critical for forming a stable protective oxide layer, which prevents the steel from scaling in high-temperature steam environments. Molybdenum acts as a solid-solution strengthener and also forms stable carbides (such as M₂₃C₆) that pin grain boundaries, effectively slowing down the **dislocation climb** that characterizes creep deformation. This synergy makes 1.7380 far superior to lower alloy grades like 13CrMo4-5 (1.7335).

2. Mechanical Properties and High-Temperature Performance

Engineers select 1.7380 primarily for its mechanical stability. At room temperature, the material exhibits high ductility and toughness, but its true value lies in its **Yield Strength** and **Tensile Strength** at temperatures exceeding 400°C.

Property	Value (at Room Temp)
Tensile Strength (Rm)	480 - 630 MPa
Yield Strength (ReH)	min. 280 MPa
Elongation (A5)	min. 18%
Impact Energy (ISO-V)	min. 31 J

Temperature-Dependent Yield Strength

As service temperatures rise, the permissible stress levels for 10CrMo9-10 must be downgraded according to established safety factors. The following is an approximation of the minimum 0.2% proof strength at elevated temperatures:

- 300°C: 205 MPa
- 400°C: 175 MPa
- 500°C: 140 MPa
- 550°C: 110 MPa

3. Creep Resistance and the Larson-Miller Parameter

In power plant design, the lifetime of a component is often dictated by **creep**—the slow, permanent deformation of a material under constant stress at high temperatures. For 1.7380, the creep rupture strength is a fundamental design criterion. To predict the long-term behavior of 10CrMo9-10, engineers utilize the **Larson-Miller Parameter (LMP)**.

The formula for LMP is defined as:

$LMP = T(C + \log t_{r})$

Where:

- **T** is the absolute temperature (in Kelvin or Rankine).
- **C** is a material constant (usually around 20 for this alloy).
- **t_{r}** is the time to rupture (in hours).

By using this model, designers can determine that at 500°C, a stress level of approximately 80 MPa will lead to a 100,000-hour rupture life. This predictability is what makes 1.7380 a preferred choice for **superheater tubes** and **main steam piping** in coal and gas-fired power stations.

4. Fabrication: Heat Treatment and Welding Procedures

10CrMo9-10 is a perlitic-ferritic steel that is sensitive to cooling rates. Proper thermal processing is mandatory to achieve the desired microstructure and prevent hydrogen-induced cracking (HIC) during welding.

Standard Heat Treatment Cycles

1. Normalizing: Heated to 900°C - 960°C, followed by cooling in air or in a protective atmosphere. This refines the grain structure.
2. Tempering: Heated to 680°C - 750°C. This is crucial for achieving the required toughness and

reducing internal stresses.

3. Stress Relieving: Typically performed after welding at temperatures slightly below the tempering temperature (approx. 650°C - 700°C).

Welding Guidelines

Welding 1.7380 requires strict adherence to preheat and post-weld heat treatment (PWHT) protocols. Because the alloy has high hardenability, the heat-affected zone (HAZ) can become brittle if cooled too quickly.

- Preheating: Depending on the wall thickness, a preheat of 200°C to 300°C is generally required to drive off moisture and slow down the cooling rate.
- Filler Metals: Use low-hydrogen consumables such as E9018-B3 (for SMAW) or ER90S-B3 (for GTAW/GMAW). These filler metals match the 2.25Cr-1Mo composition of the base metal.
- PWHT: Post-weld heat treatment is mandatory for most pressure vessel codes (such as ASME Section VIII or EN 13445). It ensures the HAZ is tempered to a hardness level typically below 240 HV, reducing the risk of stress corrosion cracking.

5. Global Equivalents and Standards Comparison

In the global supply chain, material specifications often transition between European (EN) and American (ASTM/ASME) standards. Understanding these equivalents is vital for international projects.

Standard	Grade Designation	Product Form
EN 10216-2 / 10273	1.7380 (10CrMo9-10)	Tubes / Bars / Forgings
ASTM A335	P22	Seamless Pipe
ASTM A182	F22	Forged Flanges & Fittings
ASTM A213	T22	Boiler / Superheater Tubes
DIN	10CrMo910	Old German Standard

While these grades are often treated as interchangeable, it is important to check specific project requirements, as there may be subtle differences in the maximum allowable phosphorus and sulfur content or specific impact testing requirements between EN and ASTM standards.

6. Resistance to Hydrogen Attack (Nelson Curves)

In the petrochemical industry, 1.7380 is frequently used in **hydroprocess units** where the steel is exposed to high-pressure hydrogen at elevated temperatures. In such environments, carbon steel is susceptible to **High-Temperature Hydrogen Attack (HTHA)**, where hydrogen reacts with the carbon in the steel to form methane gas. This creates internal fissures and catastrophic failure.

The 2.25% Chromium and 1% Molybdenum in 10CrMo9-10 provide significantly higher resistance to HTHA compared to carbon-moly steels. According to the **API RP 941 (Nelson Curves)**, 1.7380 can safely operate at much higher partial pressures of hydrogen and higher temperatures, making it a staple for desulfurization reactors and hydrocrackers.

7. Case Study: Failure Modes and Troubleshooting

Despite its robustness, 1.7380 is not immune to failure if operated outside its design envelope. Understanding these failure modes is essential for maintenance and life-extension programs.

Graphitization

While 1.7380 is more resistant than carbon steel, prolonged exposure to temperatures above 425°C can lead to **graphitization**, where the iron carbides break down into graphite nodules. These nodules weaken the steel. However, the high Chromium content in 10CrMo9-10 effectively inhibits this process, which is why it is preferred over the lower-chrome P11 (1.25% Cr) grade.

Creep Cavitation

In aging power plants, 1.7380 components may develop micro-voids at the grain boundaries, known as creep cavitation. **Non-Destructive Testing (NDT)**, such as surface replication (metallography), is used during plant outages to detect these voids. If the cavitation progresses to "macro-cracking," the component must be replaced immediately to avoid a steam explosion.

Thermal Fatigue

In plants that undergo frequent start-stop cycles (cycling plants), the thick-walled sections of 1.7380 headers can suffer from thermal fatigue. The relatively low thermal conductivity of the alloy (compared to carbon steel) leads to

high temperature gradients and resultant cyclical stresses. Proper **ramp-up** and **cool-down** procedures are the primary defense against this mode of failure.

8. Implementation Field Guide: Selection and Procurement

When specifying 1.7380 for a project, several critical factors must be addressed in the Purchase Description to ensure quality:

1. Certification: Require EN 10204 3.1 or 3.2 certification to verify chemical and mechanical properties.
2. Hardness Limits: Specify a maximum hardness (e.g., 225 HB) to ensure the material is in a fully tempered condition.
3. Grain Size: For high-temperature creep applications, a coarse grain size is sometimes preferred, whereas for toughness at lower temperatures, a fine grain size is better.
4. NDT Requirements: Specify ultrasonic testing (UT) for thick plates or forgings to check for internal laminations or inclusions.

Comparative Evaluation: 1.7380 vs. 1.4903 (P91)

For even higher temperatures (up to 620°C), engineers may consider **Grade 91 (1.4903)**. However, 1.7380 remains more common due to its lower cost and easier fabrication. P91 requires much tighter control over heat treatment and is more susceptible to "Type IV" cracking in the weld zones.

Feature	1.7380 (10CrMo9-10)	1.4903 (X10CrMoVNb9-1)
Max Service Temp	~580°C	~620°C
Weldability	Good (with preheat/PWHT)	Difficult (Extremely sensitive)
Relative Cost	Baseline (1.0x)	Approx. 2.5x - 3x
Creep Strength	Moderate-High	Very High

9. Summary of Engineering Implications

The material 1.7380 (10CrMo9-10) represents a peak in the evolution of low-alloy steels. Its chemical synergy of Chromium and Molybdenum provides a robust defense against the primary enemies of high-temperature equipment: oxidation, creep, and hydrogen attack. While the industry is seeing a shift toward high-chromium martensitic steels (like P91) and nickel-based superalloys for ultra-supercritical power plants, 1.7380 remains the "workhorse" for standard power generation and chemical processing units worldwide.

Its reliability is not just a product of its chemistry, but also of the rigorous standards governing its fabrication. By strictly adhering to normalized-tempered heat treatments and mandatory post-weld stress relief, engineers can ensure that components made from 1.7380 deliver a service life exceeding 25 years. As energy demands continue to grow and existing infrastructure ages, the technical mastery of this alloy will remain a vital competency for engineers across the globe. Whether used in a boiler drum, a high-pressure steam pipe, or a chemical reactor, 1.7380 stands as a testament to the effectiveness of precision metallurgy in the face of extreme operational demands.

Baca Juga (Artikel Terkait)

- [Comprehensive Engineering Guide to Polyurethane Elastomers in the Automotive Industry](http://alaskawriters.com/polyurethane-elastomers-automotive-engineering-guide.pdf)

URL: <http://alaskawriters.com/polyurethane-elastomers-automotive-engineering-guide.pdf>

- [Comprehensive Guide to ALCOA 6061: Metallurgy, Mechanical Properties, and Industrial Applications](http://alaskawriters.com/alcoa-6061-aluminum-alloy-comprehensive-technical-guide.pdf)

URL: <http://alaskawriters.com/alcoa-6061-aluminum-alloy-comprehensive-technical-guide.pdf>

- [The Definitive Guide to Engineered Materials: Properties, Selection, and Technical Applications of Advanced Nonmetallics](http://alaskawriters.com/engineered-materials-handbook-technical-guide.pdf)

URL: <http://alaskawriters.com/engineered-materials-handbook-technical-guide.pdf>

- [The Definitive Guide to Nonferrous Alloys: Properties, Selection, and Industrial Applications](http://alaskawriters.com/guide-to-nonferrous-alloys-properties-selection.pdf)

URL: <http://alaskawriters.com/guide-to-nonferrous-alloys-properties-selection.pdf>

Tags: #1.7380 #10CrMo9 10 #Alloy Steel #Creep Resistance #Pressure Vessels #ASTM A335 P22

